



PRODUCT DATA SHEET

PRODUCT: Clear Field Applied Acrylic
OBJECT FINISHED: Cementitious substrates

FORMULA NUMBER: 96H-177

WEIGHT/GALLON:	8.61 lbs.	RECOMMENDED REDUCTION:	None
VISCOSITY:	25-35 Zahn #2	REDUCER:	None
GRIND:	N/A	REDUCED VISCOSITY:	Use as supplied
WEIGHT SOLIDS:	24.5%	RECOMMENDED FILM THICKNESS:	
V.O.C.:	.14 lbs/gal minus exempt .03 lbs/gal as supplied .14 lbs/volume solid	WET:	4-6 mils
VOLUME SOLIDS:	23.4%	DRY:	1.0-1.5 mils
COVERAGE:	375 ft ² /gal @ 1 mil dry	FLASH TIME:	15 minutes
SUBSTRATE PREP.:	Clean and dry	BAKE TIME:	Air dry
APPLICATION METHOD:	Spray, brush or roll	BAKE TEMPERATURE	N/A
EQUIPMENT SETTINGS:	Adjust as needed to apply a smooth, continuous film.	OVEN TYPE:	Air dry
APPLIED OVER:	Clean substrate	GLOSS:	Full
USED UNDER:	N/A	HARDNESS:	N/A
		IMPACT RESISTANCE:	N/A

REMARKS: This product was designed for use as a protective and decorative coating for cementitious substrates. It is water and UV resistant. It dries quickly to a hard, durable film with good adhesion.

DATE ISSUED: 4/28/06

COMPLETED BY: S. Sander